



POLIFOR L30 GF/30 NATURALE AA130122S

Polypropylene Compound (PP)

Description	Polypropylene homopolymer reinforced with 30% chemically coupled glass fiber
Color	Natural
Norm compliance	Compliant with Regulation (EC) No 1907/2006 (REACH)
Certifications	UL product certified - File E187982
Processing technology	Injection moulding

Physical properties	Typical value	Units	Test Method
MFI Melt Flow Index 230°C/2,16kg	13	g/10min	ASTM D1238
Density	1.13	g/cm ³	ASTM D792
Mold Shrinkage	0.3	%	INTERNAL
Mechanical properties	Typical value	Units	Test Method
Tensile strength at yield	82	MPa	ASTM D638
Tensile elongation at break	3.5	%	ASTM D638
Flexural Modulus	5600	MPa	ASTM D790
IZOD impact strength, notched (23 °C)	90	J/m	ASTM D256
Thermal properties	Typical value	Units	Test Method
Vicat Softening Temperature B (50°C/h at 50 N)	138	°C	ASTM D1525
HDT Heat Deflection Temperature A (1,82 MPa)	150	°C	ASTM D648
Ball Pressure Temperature	125	°C	IEC 335
Flammability	Typical value	Units	Test Method
Flame Rating (1,6 mm)	HB	Class	UL94
Flame Rating (3,2 mm)	HB	Class	UL94
GWIT (Glow Wire Ignition Temperature)	650	°C / mm	IEC 60695-2-13
Electrical properties	Typical value	Units	Test Method
CTI Comparative tracking index	600	VOLT	IEC 60112

Processing conditions	Typical value
Drying not necessary	

Injection moulding	Typical value
Recommended processing temperatures:	
1st Zone	210°C
2nd Zone	230°C
3rd Zone	240°C
Mould	50-70°C

Storage

This product should be stored in a covered facility and kept away from moisture and heat.

Disclaimer

The figures reported in this Technical Data Sheet are based on tests and analyses carried out in SO.F.TER. laboratories on injection-moulded specimens. These figures indicate the typical material properties and are not to be considered a specification. The user shall always carry out his own tests and analyses in order to verify the suitability of the material for the specific application. Test carried out at 23°C unless otherwise stated.

For technical or commercial information:**EUROPE**

SO.F.TER. SPA, Via Mastro Giorgio 1, 47122 Forlì, Italy, tel +39 0543 790411
info.it@softergroup.com

USA

SO.F.TER. USA, 400 Innovative Way, Lebanon, TN 37090, US, tel +1 844 657 6383 (THINKSOFTER)
info.us@softergroup.com

BRAZIL

SO.F.TER. BRASIL, Av. Edgar Hoffmeister, 275, CEP 93700-000, Campo Bom, RS, Brazil, tel +55 51 2123 2610
info.br@softergroup.com

MEXICO

SO.F.TER MEXICO, Circuito Mexiamora Norte 345, Puerto Interior, Silao, G.to, Mexico 36275, tel +52 472 722 6923